

Description

Total Petrochemicals PPR 3221 is a random copolymer polypropylene with a Melt Flow Index of 1.8 g/min for the manufacturing of films with outstanding optical properties and easy heat weldability in the blown process.

Polypropylene PPR 3221 is intended for food or textile packaging, for lamination films, for protection films... as well as for label films.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	1.8
Mechanical properties			
Elongation at Yield	ISO 527-2	%	<15
Flexural Modulus	ISO 178	MPa	900
Izod Impact Strength (notched)	ISO 180	KJ/m ²	
At 23°C			22
At 0°C			3.6
Hardness Rockwell – R-scale	ISO 2039-2		82
Thermal properties			
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			67
10N-50°C per hour			130
Other physical properties			
Density	ISO 1183	g/cm ³	0.902
Bulk Density	ISO 1183	g/cm ³	0.525

Additional Properties: typical film properties

	Method	Unit	Typical Value
Optical properties			
Gloss	ASTM D 2457		79
Haze	ISO 14782	%	2.1
Mechanical properties			
Tensile Strength at Yield MD *	ISO 527-3	MPa	35
Tensile Strength at Break MD *	ISO 527-3	MPa	70
Tensile Elongation at Break MD *	ISO 527-3	%	500
Dart Impact	ISO 7765-1	g	35
Elmendorf MD / TD *	ISO 6383-2	N/mm	3 / 20

* MD : Machine Direction TD : Transverse Direction