

SABIC® PP 500P

POLYPROPYLENE HOMOPOLYMER

DESCRIPTION

SABIC® PP 500P is specially developed for producing stretched tapes with following features.

- ✓ Consistent processability
- ✓ Easy orientation
- ✓ Low water carry over
- ✓ Good mechanical properties

TYPICAL APPLICATIONS

SABIC® PP 500P can be used for producing woven bags, flexible intermediate bulk containers, ropes & twines, carpet backing, geotextiles and concrete reinforcements.

TYPICAL PROPERTY VALUES

Revision 20250825

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	3	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
Molecular Weight Distribution	Broad	-	-
Isotacticity	Medium	-	-
FORMULATION			
Anti static agent	☑	-	-
Nucleating agent	☑	-	-
Gas fading stabilized	☑	-	SABIC method
MECHANICAL PROPERTIES			
Tensile test			
tensile modulus ⁽¹⁾	1550	MPa	ISO 527-2 1A
strain at yield	10	%	ISO 527-2 1A
stress at yield ⁽²⁾	37	MPa	ISO 527-2 1A
Izod impact notched			
at 23 °C	3.5	kJ/m ²	ISO 180/1A
Charpy Impact Strength Notched			
at 23 °C	4.5	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Heat deflection temperature			
at 0.45 MPa (HDT/B)	85	°C	ISO 75
at 1.80 MPa (HDT/A)	55	°C	ISO 75
Vicat Softening Temperature ⁽³⁾			
at 10 N (VST/A)	152	°C	ISO 306
at 50 N (VST/B)	88	°C	ISO 306

- (1) Speed of testing: 1 mm/min
- (2) Speed of testing: 50 mm/min
- (3) Temperature rate: 120°C/h

PROCESSING CONDITIONS

Typical processing conditions for 500P are:

Barrel temperature range: 235 - 250°C

STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.